

Machine Coated Papers

MAC367 Photogloss Paper

215 g/m²

Product Description Photogloss Paper is a single sided, cast coated, high gloss board suitable for photographic applications. It has a light matte coating on the back side.

Physical Properties	Weight	215 g/m ²	ISO 536	Acidity	7.5	pH
	Thickness	250 µm	ISO 534	Stiffness *	1711/860 mN	ISO 5628
	Whiteness	110	CIE	Porosity	2 ml/min	Bendtsen ISO5636
	Opacity	99 %	Elrepho	Roughness**	3/97 ml/min	Bendtsen ISO 8791

*MD/CD
**WS/TS

Features Advertising Material, Direct Mail, Brochures, Catalogues, Magazines, Journals, Calendars, Covers, Labels, Banners, Greeting Cards, Postcards, Point of Sale Displays, Soft Covers etc.

Available sizes	SRA3
	Grain direction SG

LG = Long grain, SG = Short grain

Storage Conditions Temperature 10 - 30 °C, Relative Humidity 20 - 70%
Repack opened reams or boxes when not in use.

Print Conditions Acclimatize paper 24 hours before printing in print room conditions (preferably next to printer)
Best results are obtained between 15-25 °C and 30 - 65% RH (relative humidity)

Environment, Health & Safety No Material Safety Data Sheet required.
ISO 9001 and 14001 certified production site.
ECF (Elemental Chlorine Free) bleaching technique for wood pulp.
Acid- lignin- and sulphur-free paper with a high degree of permanence, ISO9706 Permanent Paper certified.
Paper waste is suitable for recycling in most countries. Please refer to local paper recycle station.

Processing Guidelines, Tips & Tricks No special runnability advice.

Environmental Certification



you can

Canon



Standard disclaimer:

All specifications subject to change without notice. All company and/or product names are trademarks and/or registered trademarks of their respective manufacturers in their markets and/or countries.

Canon Inc.

canon.com

Canon Europe

canon-europe.com

Canon Europe Ltd

3 The Square, Stockley Park
Uxbridge, Middlesex
UB11 1ET UK

English Edition MMY
© Canon Europa N.V., 2014